

Sliptest Victoria Pty Ltd Accreditation Number 19858 3 Treboryn Crt, Rowville, 3178, VIC, Rowville, VIC, 3178 gary@sliptest.com.au 1300 SLIPTEST (1300 754 783)

Seamless Overlays - 02 Sep 2018

Slip Resistance Classification of New Pedestrian Surfaces - AS4586:2013 Appendix A

Date Tested:	02 Sep 2018
Test Report Number:	0209185
Client Name & Address:	Seamless Overlays - 329 Darebin Road Thornbury VIC 3071
Location of Test :	Sliptest VIctoria - 3 Treboryn Court Rowville VIC 3178
Surface / Product Tested :	Quartz Carpet Pore Filled 1-2mm x 1 Coat SAD 33 x 1 Coat Topline Matt
Wet Pendulum Test carried out using :	Slider 96 (4S) Rubber slider
Record ambient temperature (°C)	13
Fixed / Unfixed Test :	No - Tested in the Direction of least Anticipated Slip Resistance
Testing Officer:	Gary Wiltshire
Testing Officer Signature	GMMM2

Accedited for Compliance with ISO/IEC 17025. The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited.

Test Results:

	Mean BPN of last 3 swings :	Image of Surface
Test 1	29	Q455 775 873
Test 2	28	CALSO, 758 EST2

Seamless Overlays - Page 1

	Mean BPN of last 3 swings :	Image of Surface
Test 3	28	8436-718-057
Test 4	30	Q436 738 832
Test 5	28	CATAL TIME STATE
Mean BPN	I Slip Resistance Value (SRV)	29

P2 = 25 - 34

Seamless Overlays - Page 2

Using Slider 96 (4S) you have achieved a BPN of