

VOC Content in X-BOND Liquid

File number : 01-0624-19
Subject : VOC content in X-Bond Liquid

VOC content has been tested by 3rd party laboratory

Test methods

ASTM D-3960 : This practice discusses applicable ASTM test methods used in the determination of the VOC content of paints and related coatings and provides equations for calculating the VOC content expressed as the mass of VOC: (1) per unit volume of coating less water and exempt volatile compounds, and (2) per unit volume of coating solids and (3) per unit mass of coating solids.

ASTM D-3792 : In order to calculate volatile organic content (VOC) in waterborne paints, it is necessary to know the water content. This gas chromatographic test method provides a relatively simple and direct way to determine water content.

ASTM D-4457 : Use of 1,1,1-trichloroethane and dichloromethane, which do not measurably contribute to the atmospheric oxidant level, is a way for industry to meet government or other regulations on volatile organic compounds.

This test method is designed to determine the content of these halohydrocarbon solvents in paints and coatings. That content can subsequently be used in calculating the volatile organic compound content of a coating.

ASTM D-2369 : This test method is the procedure of choice for determining volatiles in coatings for the purpose of calculating the volatile organic content in coatings under specified test conditions. The weight percent solids content (nonvolatile matter) may be determined by difference. This information is useful to the paint producer and user and to environmental interests for determining the volatiles emitted by coatings.

ASTM D-1475 : This test method is suitable for the determination of density of paint and related products and components when in liquid form. It is particularly applicable when the fluid has too high a viscosity or when a component is too volatile for a density balance determination.

SAMPLE ID : XB800 X-Bond Liquid (1 quart) ID : 8060211-01 Sampled : 06/ 11/19							
Analyte	Results	Flag	Units	PQL	Prep/Test Method	Analyzed	Batch
Volatile Organic Content	256		g/l	2.00	ASTM D-3960	06/24/2019	BG80319
Volatile Organic Content	2.13		lbs/gal	0.0210	ASTM D-3960	06/24/2019	BG80319
VOC in Solids	509		g/l	2.00	ASTM D-3960	06/24/2019	BG80319
VOC in Solids	4.24		lbs/l	0.0210	ASTM D-3960	06/24/2019	BG80319
Water Content	48.9		%	2.00	ASTM D- 3792	06/24/2019	BG80319
Exempt Solvent	ND		%	2.00	ASTM D-4457	06/24/2019	BG80319
Non Volatile Residue	25.9		%	0.100	ASTM D-2369	06/24/2019	BG80319
Density	1.015		g/ml		ASTM D-1475	06/24/2019	BG80319

NA Not Applicable
ND Analyte NOT DETECTED at or above detection limit
NR Not Reported
MDL Method Detection Limit
PQL Practical quantitation Limit

PRECAUTIONS

Always test a small area first to determine ease of application and desired results. Gloves and eye protection should be worn during application. Do not mix with other cleaners. Not for use on humans or animals. If any contact with skin or eyes occurs, wash immediately with plenty of water. Be sure to read container label and Material Safety Data Sheet before using this product.

LIMITED WARRANTY NOTICE

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance to SEMCO Post Matrix procedure, recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Federal, state and local specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request.

